

Amendments to the Claims

This listing of claims will replace all prior listings of claims in the application.

Listing of Claims

order  
OK

1.-9. (Canceled)

10. (Currently Amended) A metalized molded product comprising a molded product made of a thermoplastic resin composition comprising 90-30% by weight of (A) a thermoplastic resin consisting of a blend of (1) a polyamide, (2) a styrene polymer selected from the group consisting of high-impact polystyrene, an acrylonitrile-butadiene-styrene copolymer, an acrylonitrile-styrene copolymer and a styrene-butadiene copolymer and (3) a copolymer of a carboxy group-containing unsaturated compound and styrene, 5-60% by weight of (B) a fibrous filler and 5-60% by weight of (C) a whisker and a metal plating provided on the molded product.

22 11. (Previously Presented) The metalized molded product of Claim 10, wherein the fibrous filler is carbon fiber.

33 12. (Previously Presented) The metalized molded product of Claim 10, wherein the thermoplastic resin composition further comprises a flame retardant.

44 13. (Previously Presented) The metalized molded product of Claim 12, wherein the flame retardant is at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

55 14. (Previously Presented) The metalized molded product of Claim 10, wherein the thermoplastic resin is at least one

member selected from the group consisting of a polyamide and an ABS resin.

6 15. (Previously Presented) The metalized molded product of Claim 14, wherein the thermoplastic resin is an ABS resin.

16.-18. (Canceled)

7 7 19. (Previously Presented) The metalized molded product of Claim 13, wherein the flame retardant is a hydrated metal flame retardant.

20. (Canceled)

8 8 21. (Previously Presented) The metalized molded product of Claim 10, wherein the thermoplastic resin composition comprises 90-30% by weight of (A) a thermoplastic resin comprising at least one member selected from the group consisting of a polyamide and a styrene polymer, 5-60% by weight of (B) carbon fiber, 5-60% by weight of a whisker having a specific gravity of at least 2 and a flame retardant comprising at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

9 9 22. (Previously Presented) The metalized molded product of Claim 21, wherein the thermoplastic resin is an ABS resin and the flame retardant is a hydrated metal flame retardant.

AS 10 10 23. (New) The metalized molded product of Claim 10, wherein the styrene polymer is selected from the group consisting of high-impact polystyrene, acrylonitrile-butadiene-styrene copolymer and styrene-butadiene copolymer. ABS

SB 11 24. (New) The metalized molded product of Claim 10, wherein the polyamide is nylon 6, the styrene polymer is an

Does not meet

acrylonitrile-butadiene-styrene copolymer and the copolymer of a carboxy group-containing unsaturated compound and styrene is a maleic acid-modified acrylonitrile-butadiene-styrene copolymer.

12/26. (New) The metalized molded product of Claim 10, wherein the fibrous filler is a carbon filler and the whisker is aluminum borate whisker.

13/26. (New) The metalized molded product of Claim 12, wherein the flame retardant is a hydrate of an alkali metal or an alkaline earth metal.

14/27. (New) The metalized molded product of Claim 12, wherein the flame retardant is magnesium hydroxide.

15/28. (New) The metalized molded product of Claim 10, wherein the polyamide is nylon 6, the styrene polymer is an acrylonitrile-butadiene-styrene copolymer, the copolymer of a carboxy group-containing unsaturated compound and styrene is a maleic acid-modified acrylonitrile-butadiene-styrene copolymer, the filler is carbon fiber, the whisker is aluminum borate whisker and a red phosphorus flame retardant is present in the thermoplastic resin composition.

Amendments to the Claims

This listing of claims will replace all prior listings of claims in the application.

Listing of Claims

Claims 1-9 (Cancelled)

10. (Previously Presented) A metalized molded product comprising a molded product made of a thermoplastic resin composition comprising 90-30% by weight of (A) a thermoplastic resin, 5-60% by weight of (B) a fibrous filler and 5-60% by weight of (C) a whisker and a metal plating provided on the molded product.

11. (Previously Presented) The metalized molded product of Claim 10, wherein the fibrous filler is carbon fiber.

12. (Previously Presented) The metalized molded product of Claim 10, wherein the thermoplastic resin composition further comprises a flame retardant.

13. (Previously Presented) The metalized molded product of Claim 12, wherein the flame retardant is at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

14. (Previously Presented) The metalized molded product of Claim 10, wherein the thermoplastic resin is at least one member selected from the group consisting of a polyamide and an ABS resin.

15. (Previously Presented) The metalized molded product of Claim 14, wherein the thermoplastic resin is an ABS resin.

Claims 16-18 (Cancelled)

19. (Previously Presented) The metalized molded product of Claim 13, wherein the flame retardant is a hydrated metal flame retardant.

Claim 20 (Cancelled)

21. (New) The metalized molded product of Claim 10, wherein the thermoplastic resin composition comprises 90-30% by weight of (A) a thermoplastic resin comprising at least one member selected from the group consisting of a polyamide and a styrene polymer, 5-60% by weight of (B) carbon fiber, 5-60% by weight of a whisker having a specific gravity of at least 2 and a flame retardant comprising at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

22. (New) The metalized molded product of Claim 21, wherein the thermoplastic resin is an ABS resin and the flame retardant is a hydrated metal flame retardant.

09/86 9,747

Amendments to the Claims

This listing of claims will replace all prior listings of claims in the application.

Listing of Claims

Claims 1-9 (Cancelled)

10. (Previously Presented) A metalized molded product comprising a molded product made of a thermoplastic resin composition comprising 90-30% by weight of (A) a thermoplastic resin, 5-60% by weight of (B) a fibrous filler and 5-60% by weight of (C) a whisker and a metal plating provided on the molded product.

TP  
fiber  
whisker

11. (Previously Presented) The metalized molded product of Claim 10, wherein the fibrous filler is carbon fiber.

12. (Previously Presented) The metalized molded product of Claim 10, wherein the thermoplastic resin composition further comprises a flame retardant.

13. (Previously Presented) The metalized molded product of Claim 12, wherein the flame retardant is at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

14. (Previously Presented) The metalized molded product of Claim 10, wherein the thermoplastic resin is at least one member selected from the group consisting of a polyamide and an ABS resin.

15. (Previously Presented) The metalized molded product of Claim 14, wherein the thermoplastic resin is an ABS resin.

Claims 16-18 (Cancelled)

428/458

462

474.4

323

19. (Previously Presented) The metalized molded product of Claim 13, wherein the flame retardant is a hydrated metal flame retardant.

Claim 20 (Cancelled)

21. (New) The metalized molded product of Claim 10, wherein the thermoplastic resin composition comprises 90-30% by weight of (A) a thermoplastic resin comprising at least one member selected from the group consisting of a polyamide and a styrene polymer, 5-60% by weight of (B) carbon fiber, 5-60% by weight of a whisker having a specific gravity of at least 2 and a flame retardant comprising at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

22. (New) The metalized molded product of Claim 21, wherein the thermoplastic resin is an ABS resin and the flame retardant is a hydrated metal flame retardant.



IN THE CLAIMS

old

Please cancel Claims 1-7.

Please add new Claims 8-20 as follows.

B'

8. (New) A thermoplastic resin composition comprising 90-30% by weight of (A) a thermoplastic resin selected from the group consisting of a polyamide and a styrene polymer, 5-60% by weight of (B) a fibrous filler and 5-60% by weight of (C) a whisker.

9. (New) The thermoplastic resin composition of Claim 8, wherein the styrene polymer is an ABS resin.

10. (New) A metalized molded product comprising a molded product made of a thermoplastic resin composition comprising 90-30% by weight of (A) a thermoplastic resin, 5-60% by weight of (B) a fibrous filler and 5-60% by weight of (C) a whisker and a metal plating provided on the molded product.

11. (New) The metalized molded product of Claim 10, wherein the fibrous filler is carbon fiber.

12. (New) The metalized molded product of Claim 10, wherein the thermoplastic resin composition further comprises a flame retardant.

13. (New) The metalized molded product of Claim 12, wherein the flame retardant is at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

14. (New) The metalized molded product of Claim 10, wherein the thermoplastic resin is at least one member



selected from the group consisting of a polyamide and an ABS resin.

B1  
Cont.  
15. (New) The metalized molded product of Claim 14, wherein the thermoplastic resin is an ABS resin.

16. (New) A thermoplastic resin composition comprising 90-30% by weight of (A) a thermoplastic resin comprising at least one member selected from the group consisting of a polyamide and a styrene polymer, 5-60% by weight of (B) carbon fiber, 5-60% by weight of a whisker having a specific gravity of at least 2 and a flame retardant comprising at least one member selected from the group consisting of a red phosphorus flame retardant and a hydrated metal flame retardant.

17. (New) The thermoplastic resin composition of Claim 16, wherein the thermoplastic resin is an ABS resin.

18. (New) The thermoplastic resin composition of Claim 8, additionally comprising a hydrated metal flame retardant.

19. (New) The metalized molded product of Claim 13, wherein the flame retardant is a hydrated metal flame retardant.

20. (New) The thermoplastic resin composition of Claim 16, wherein the flame retardant is a hydrated metal flame retardant.

---